

NEPCOAT- Qualified Products List

for Protective Coatings for New and 100% Bare Existing Steel for Bridges

Nepcoat System No.	Coats	PRODUCTS - TESTED AND ACCEPTED	Slip Coef Class	Recom'd DFT (min/max) mil	Coating (micron)	VOC (Delivered) lb/gal	g/L	QPL Approval Dates
<u>NEPCOAT SYSTEM A - INORGANIC zinc rich primer / epoxy or urethane intermediate / aliphatic urethane finish</u>								
A7-97	(T30)	CARBOLINE COMPANY						from
	Primer	Carbo Zinc 11 HS	B	2-3	50-75	2.4	288	3/3/99
	Inter	Carboline 893 Epoxy Intermediate		4-6	100-150	1.6	195	until
	Finish	Carbothane 133 HB Aliphatic Polyurethane		3-5	75-125	3.2	384	3/3/03
A8-97*	(T36)	INTERNATIONAL PROTECTIVE						from
	Primer	Interzinc 22 HS IOZ Silicate	B	2-3	50-75	2.8	340	3/30/00
	Inter	Intergard 475 HS Epoxy		5-8	125-200	1.5	175	until
	Finish	Interthane 990 HS Polyurethane		2-3	50-75	2.7	327	3/30/03
A9 -97	(T47)	AMERON PROTECTIVE COATINGS						from
	Primer	Dimetcote D9 HS Inorganic Zinc Primer	B	3-4	75-100	2.7	320	3/28/01
	Inter	Amercoat 385 Multi-Purpose Epoxy		4-6	100-150	2.3	280	until
	Finish	Amercoat 450 HS Aliphatic Polyurethane		2-3	50-75	2.4	282	3/28/05

NOTES:

- 1 NEPCOAT-NORTHEAST PROTECTIVE COATING COMMITTEE of CT, ME, MA, NH, NJ, PA, RI, VT
- 2 Systems are accepted for use on NEW and 100% BARE EXISTING steel (cleaned by abrasive blasting) for bridges.
- 3 (Ax-94) Systems comply with NEPCOAT 94 Testing Standard (6/15/94) & Acceptance Criteria (6/5/96).
- 3 (Ax-97) Systems comply with NEPCOAT 97 Testing Standard (6/1/97) & Acceptance Criteria (3/30/00).
- 4 The -97 VOC values are provided by the testing lab. NEPCOAT max limit (3.5 lb/gal). DFT values are from manufacturer.
- 5 Any change in formulation from that tested will result in removal of the system from the QPL.
- 6 The full QPL term is four years from the date of acceptance.
- * Acceptance is CONDITIONAL pending submission within three years of successful 2-year field history.
- ** The term is extended for one year if the identical system is being retested at the end of the term.

NEPCOAT- Qualified Products List

for Protective Coatings for New and 100% Bare Existing Steel for Bridges

Nepcoat System No.	Coats	PRODUCTS - TESTED AND ACCEPTED	Slip Coef Class	Recom'd Coating DFT (min/max) mil micron	VOC (Delivered) lb/gal g/L	QPL Approval Dates
NEPCOAT SYSTEM B - ORGANIC zinc rich primer / epoxy or urethane intermediate / aliphatic urethane finish						
B7-97	(T31)	CARBOLINE COMPANY				from
	Primer	Carboline 859 Zinc Rich Epoxy Primer	B	3-5 75-125	2.7 325	2/18/99
	Inter	Carboline 888 Epoxy Intermediate		3-5 75-125	2.8 330	until
	Finish	Carbothane 133 HB Aliphatic Polyurethane		3-5 75-125	3.2 384	2/18/03
B8-97*	(T42)	XYMAX COATINGS				from
	Primer	MonoZinc ME III Moisture Cure Primer	B	3-4 75-100	3.0 360	3/28/01
	Inter	MonoFerro PUR Moisture Cure		3-4 75-100	1.4 170	until
	Finish	Bridge Finish		2-3 50-75	3.0 362	3/28/04
B9-97*	(T45)	SHERWIN WILLIAMS				from
	Primer	Zinc Clad III HS	B	3-5 75-125	2.8 330	3/28/01
	Inter	Macropoxy 646		5-10 125-250	1.9 230	until
	Finish	Acrolon 218 Acrylic		3-6 75-150	3.3 400	3/28/04
B10-97*	(T49)	M.A.B. INDUSTRIAL COATINGS				from
	Primer	Ply-Tile Epoxy Organic Zinc Primer	A	2.5-3.5 63-88	3.5 420	3/28/01
	Inter	Ply-Mastic Epoxy		5-7 125-175	1.3 150	until
	Finish	Ply-Thane 890 HS		2-6 50-150	2.6 310	3/28/04

NOTES:

- 1 NEPCOAT-NORTHEAST PROTECTIVE COATING COMMITTEE of CT, ME, MA, NH, NJ, PA, RI, VT
- 2 Systems are accepted for use on NEW and 100% BARE EXISTING steel (cleaned by abrasive blasting) for bridges.
- 3 (Bx-94) Systems comply with NEPCOAT 94 Testing Standard (6/15/94) & Acceptance Criteria (6/5/96).
- 3 (Bx-97) Systems comply with NEPCOAT 97 Testing Standard (6/1/97) & Acceptance Criteria (3/30/00).
- 4 The -97 VOC values are provided by the testing lab. NEPCOAT max limit (3.5 lb/gal). DFT values are from manufacturer.
- 5 Any change in formulation from that tested will result in removal of the system from the QPL.
- 6 The full QPL term is four years from the date of acceptance.
- * Acceptance is CONDITIONAL pending submission within three years of successful 2-year field history.
- ** The term is extended for one year if the identical system is being retested at the end of the term.

